

DuPont™ Active Layer

PRELIMINARY DATA

APA60015 NC000

APA60015 NC000 is a soft, very breathable, waterproof, windproof and stretchable monolithic polyester film, intended for lamination to a support fabric. Laminated fabric constructions with APA60015 NC000 have high comfort, durability and waterproofness.

Property	Test Method	Units	Value
Physical			
Film Thickness	ISO 536	micron	15
Film Unit Weight	ISO 536	g/m ²	18
Mechanical			
Tensile Strength at Break	ASTM D 882	MPa (kpsi)	14 (2)
Machine direction, Film			
Transverse direction, Film			14 (2)
Elongation at Break	ASTM D 882	%	460
Machine direction, Film			
Transverse direction, Film			620
Hydrostatic Resistance	ASTM D 751-95	m	>10
Mullen Burst			
Elastic Modulus	ISO 527-1/-3	MPa (kpsi)	44 (6.4)
Propagation Tear Resistance	ASTM D 1922	mN (lbf)	60 (0.014)
Machine direction, Film			
Transverse direction, Film			105 (0.024)
Initial Tear Resistance	ASTM D 1004	N/mm (lb/in)	60 (340)
Machine direction, Film			
Transverse direction, Film			75 (425)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, and The miracles of science™ are trademarks or registered trademarks of DuPont Company. Copyright© 2008

080826/080826

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3

Product Information

APA60015 NC000

Property	Test Method	Units	Value
Permeability			
Water Vapor Transmission Rate 24°C, 55%RH	ASTM E 96B	g/m ² /day	900
Water Vapor Transmission Rate 24°C, 55%RH	ASTM E 96BW	g/m ² /day	15,000
Water Vapor Transmission Rate	ISO 15496	g/m ² /day	16,000
Water Vapor Transmission Rate up-cup	JIS L1099 A-1	g/m ² /day	6000
Thermal			
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	200 (392)
Vicat Softening Temperature 10N, 50°C/h	ISO 306	°C (°F)	151 (303)
Optical			
Haze	ASTM D 1003-97	%	90
Other			
Hardness, Shore D Resin	ISO 868		45
Processing			
Dimensional Stability 180°C, 15min		%	0.0

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
Test temperatures are 23°C unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, and The miracles of science™ are trademarks or registered trademarks of DuPont Company. Copyright© 2008

080826/080826

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3