

## DuPont™ Artistri™ Ink - End Use Properties Data

**Ink Type:** DuPont™ Artistri™ 500 Series Pigment Sampling Ink

**Fabric Type:** Cotton

		Individual Ink Results						
Test Name	Test ID Number	C P576	M P513	Y P545	K P593	R P526	G P569	V P582
Wash Fastness(50C)	AATCC 61 (ISO105-C06)							
	shade change	1-2	2	3-4	3-4	3	2-3	3-4
Light Fastness (Xenon Lamp 60 hrs.)	AATCC 16 (ISO 105-B02)	5	4-5	1	5	4-5	4-5	4-5
Light Fastness (Xenon Lamp 20 hrs.)	AATCC 16 (ISO 105-B02)	4-5	4-5	3	5	4-5	4-5	4-5
Wet and Dry Crockfastness	AATCC 8 (ISO 105-X12)	1/2-3	1/1-2	2-3/3-4	1/2	1-2/2-3	2/3	1/2



The miracles of science™

DuPont Imaging Technologies  
 Barley Mill Plaza P.O. Box 80030  
 Wilmington, DE 19880-0030  
 US 1.877.234.1794 or 1.302.992.4264  
 ASIA +65.6586.3699  
 EUROPE +39.02.9542.4456  
[www.artistri.dupont.com](http://www.artistri.dupont.com)

The information has been carefully compiled from experience gained in the laboratory and under commercial conditions. However, the product's performance and its suitability for the customer's purpose depend on the particular conditions of use. We recommend that customers satisfy themselves that each product meets their requirements in all respects. This information is being provided by DuPont free of charge as a courtesy to DuPont's customers, and DuPont HEREBY DISCLAIMS ALL REPRESENTATIONS, WARRANTIES AND LIABILITIES WITH RESPECT TO THE INFORMATION AND USE THEREOF. Subject to change without notice. All sales are subject to our standard terms and conditions of sale. Copyright © 2003 Rev. 2004, 2006. The DuPont Oval, DuPont™, The miracles of science™ and Artistri™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates. All rights reserved. K-05988-2 01/07