

# DuPont™ Elvanol® 70-62

## POLYVINYL ALCOHOL

### Product Data Sheet

#### Description

Elvanol® 70-62 is a high viscosity, fully hydrolyzed polyvinyl alcohol (PVOH) designed to provide high films with exceptional high tensile strength and tear resistance, with excellent resistance to oil, grease, petroleum hydrocarbons and other common solvents. High viscosity polyvinyl alcohol is more effective than lower viscosity polyvinyl alcohol in adhesives on a pound for pound basis.

#### Typical Properties of Elvanol® 70-62

Viscosity, cps <sup>1</sup>	58.0-68.0
Solution, pH	5.0-7.0
Percent hydrolysis <sup>2</sup>	99.4-99.8
Volatiles, wt. % max.	5.0
Ash, wt. % max. <sup>3</sup>	0.70

<sup>1</sup> Viscosity in mPa.s (cP) of a 4% solids aqueous solution at 20° C (68°F)

<sup>2</sup> Mole percent hydrolysis of acetate groups, dry basis

<sup>3</sup> Dry basis, calculated as % Na<sub>2</sub>O

#### Resin Characteristics

Elvanol® 70-62 is a high viscosity, fully hydrolyzed grade of polyvinyl alcohol. It is a white granular powder soluble in hot water, but insoluble in cold water and common organic solvents. Elvanol® 70-62 exhibits excellent adhesion to various materials, particularly paper, paperboard, leather, and other porous substrates and provides bonds with excellent water resistance.

#### Suggested Uses

Elvanol® 70-62 is particularly recommended for formulating low cost adhesives used in bonding cellulosic substrates. Applications include laminating adhesives for the manufacture of solid fiberboard and laminated specialties. Other applications are paper and paperboard sizing to provide strength and water resistance to these substrates as well as adhesive binders for non-woven fabrics, clays, pigments, cork, ceramic materials and various other solid particles.

#### FDA Status

Elvanol® 70-62 polyvinyl alcohol complies with U.S. Food and Drug Administration (FDA) Regulations under the following Sections of Title 21 CFR, and may be used in contact with food, subject to the limitations and requirements therein:

- 175.105 - Adhesives
- 175.300 - Resinous and polymeric coatings <sup>(1)</sup>
- 175.320 - Resinous and polymeric coatings for polyolefin films <sup>(2)</sup>
- 176.170(b) - Components of paper and paperboard in contact with aqueous and fatty foods <sup>(3)</sup>
- 176.180 - Components of paper and paperboard in contact with dry food <sup>(4)</sup>
- 177.1200 - Cellophane
- 177.1670 - Polyvinyl alcohol film <sup>(5)</sup>
- 177.2260 - Filters, resin-bonded <sup>(6)</sup>
- 177.2800 - Textiles and textile fibers <sup>(7)</sup>

(1) Subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c).

(2) For use only as a dispersing agent at levels not to exceed 6 percent of total coating weight in coatings for polyolefin films provided the finished polyolefin films contact food only of Types V, VII and IX (identified in 21 CFR 176.170(c), Table 1), subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c).

(3) Subject to the finished food-contact surface of the paper or paperboard meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation.

(4) As a component of the uncoated and coated food-contact surface of paper and paperboard in contact with dry food (Food Type VIII, identified in 21 CFR 176.170(c), Table 1).

(5) In the preparation of polyvinyl alcohol film that may be used in contact with food of Types V, VIII and IX (identified in 21 CFR 176.170(c), Table 1), provided the food-contact film in contact with food Types V or IX is subject to the finished food-contact surface of the paper or paperboard meeting the extractive limitations under the intended conditions of use, as shown in paragraph (b) of the Regulation. The finished food-contact film shall not be used as a component of food containers intended for use in contact with water.

(6) Subject to the finished resin-bonded filter meeting the extractive limitations under the intended conditions of use, as shown in the Regulation. In accordance with good manufacturing practice, finished filters should be thoroughly cleansed prior to their first use in contact with food.

(7) For use in textiles and textile fibers that may be used as articles or components of articles in contact with dry food (Food Type VIII, identified in 21 CFR 176.170(c), Table 1).



The miracles of science™

## Safety & Handling

Read and understand the Materials Safety Data Sheet (MSDS) before using this product. Elvanol® 70-62 is technical quality polyvinyl alcohol. It is not recommended for inclusion in any food or preparation that might be taken internally.

Under certain conditions of use, dust may be formed from Elvanol® polyvinyl alcohol. DuPont recommends that dust from Elvanol® be treated as a nuisance dust, which is regulated by the Occupational Safety and Health Administration (OSHA) under Title 29, Code of Federal Regulations, Section 1910.1000. Under this section, an employee's exposure to nuisance dust shall be limited to 15 milligrams per cubic meter (mg/m<sup>3</sup>) of total dust and 5 mg/m<sup>3</sup> of respirable dust on a time-weighted average in any 8-hour shift of a 40-hour week.

The DuPont limit for polyvinyl alcohol exposure to nuisance dust is 10 mg/m<sup>3</sup>, and for respirable dust is 5 mg/m<sup>3</sup>. If excessive concentrations of dust are encountered, a mask or respirator and goggles should be worn. The mask or respirator should comply with Section 1910.134 of the OSHA regulations; the goggles should comply with Section 1910.133.

For bulk storage and handling of Elvanol® (e.g. storage silos) refer to *Elvanol® Bulk Storage and Handling Safety Guide*.

Elvanol® may be disposed of by incineration or landfill. However, any disposal method must be in compliance with all applicable local, state and federal regulations.

## DuPont Offices Worldwide

### Americas

DuPont Company, BMP26-2363  
Lancaster Pike & Route 141  
Wilmington, DE 19805 U.S.A.  
Telephone +1 302 774 1161  
Toll-free (USA) 800 628 6208  
Fax +1 302 892 7390

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Telephone +55 11 4166 8542  
Fax +55 11 4166 8720

### Asia Pacific

DuPont China Holding Co, Ltd.  
15th Floor, Shui on Plaza  
333 Huai Hai Road (Central)  
Shanghai 200021, China  
Telephone +86 21 6386 6366  
Fax +65 6272 7494

### Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.  
2, Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone +41 22 717 51 11  
Fax +41 22 717 55 00

[Elvanol.dupont.com](http://Elvanol.dupont.com)

*Copyright © 2006 DuPont. All rights reserved. The technical data herein are guides to the use of DuPont resins. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary from lot to lot and with processing conditions. It is given and accepted at user's risk and confirmation of its validity and suitability in particular cases should be obtained independently. The DuPont Company makes no guarantees of results and assumes no obligations or liability in connection with its advice.*

*This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see DuPont Medical Caution Statement, H-50102.*

*The DuPont Oval, DuPont™, The miracles of science™, and Elvanol® are trademarks or registered trademarks of DuPont or its affiliates. Doc. Ref. NOL\_7062\_0601\_v3.doc*



*The miracles of science™*