

DuPont™ Entira™ AS MK 400

Entira™ AS resins Product Data Sheet

Description

Product Description Entira™ AS MK400 is an extremely hygroscopic ionomer resin that is supplied as free-flowing pellets.

Restrictions

Material Status ● Commercial: Active

Typical Characteristics

Uses ● Industrial Applications
Packaging

Features Entira™ AS MK400 is used to lower the static decay time and surface resistivity of polyolefins and other polymers.

Characteristics / Benefits Entira™ AS MK400 can be precompounded or dry blended into polymers for extrusion, molding, or various other processing methods

Applications Antistatic agent for use in films, moldings, and extruded forms.

Typical Properties

| Physical | Nominal Values | Test Method (s) | |
|-------------------------------|------------------------|-----------------|----------|
| Density () | 0.97 g/cm ³ | ASTM D792 | ISO 1183 |
| Melt Flow Rate (190°C/2.16kg) | 1.0 g/10 min | ASTM D1238 | ISO 1133 |
| Thermal | Nominal Values | Test Method (s) | |
| Melting Point (DSC) | 91°C (196°F) | ASTM D3418 | ISO 3146 |
| Freezing Point (DSC) | 61°C (142°F) | ASTM D3418 | |
| Vicat Softening Point () | 59°C (138°F) | ASTM D1525 | ISO 306 |

Processing Information

General

Maximum Processing Temperature 250°C (482°F)

General Processing Information Entira™ AS MK 400 is a very hygroscopic material. To minimize exposure to moisture, any remaining material should be hermetically sealed in a barrier package immediately after use. The bag have as much air removed as possible prior to sealing. A vacuum to pull out the air can be used to assist this process. In order to reuse remaining material that has been hermetically sealed the material should be dried under vacuum with a nitrogen flow at 50–60°C for several hours prior to use. Entira™ AS MK400 is available in pellet form for use in conventional equipment for processing polyolefins. Entira™ AS MK400 can be fed together with base polymers and other additives in the hopper during processing. Typical addition levels range from 10 - 30%.

| | |
|-------------------------------|---|
| FDA Status Information | Entira™ AS MK400 resin complies with the U.S. Food and Drug Administration Regulation 21 CFR 177.1330(a) -- Ionomeric resins, subject to the limitations and requirements therein. This Regulation describes polymers that may be in contact with food, subject to the finished food contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation. |
| Regulatory Information | For information on compliance outside the USA please contact your local DuPont representative. |
| Safety & Handling | Entira™ AS MK400 as supplied by DuPont is not considered a hazardous material. As with any hot material, care should be taken to protect the hands and other exposed parts of the body when handling molten polymer. At recommended processing temperatures, small amounts of fumes may evolve from the resins. When resins are overheated, more extensive decomposition may occur. Adequate ventilation should be provided to remove the fumes from the work area. Disposal of scrap presents no special problems and can be by landfill or incineration in a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls. For more detailed information on the safe handling and disposal of DuPont resins a Product Safety Bulletin and OSHA Material Safety Data Sheet can be obtained from the DuPont Packaging Products sales office serving you. |

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company, BMP26-2363
Lancaster Pike & Route 141
Wilmington, DE 19805 U.S.A.
Telephone +1 302-774-1161
Toll-free (USA) 800-628-6208
Fax +1 302-999-4399

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone +55 11 4166 8122
Fax +55 11 4166 8720

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2,Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

<http://entira.dupont.com>

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 09/14/2007 01:52:02 PM and supersedes all previous versions.

