

## DuPont™ Fusabond® E100BR

### Fusabond® resins Product Data Sheet

#### Description

**Product Description** DuPont™ Fusabond® E100BR is an anhydride modified high density polyethylene, mainly intended for use as a component in a blend with other polymers including polyolefins and polyamides. It is not intended for extrusion in its pure form in typical extrusions or coextrusions. Available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

#### Restrictions

**Material Status** • Commercial: Active  
**Availability** • Globally

#### Typical Characteristics

**Uses** • Polymer Modifier

#### Typical Properties

Physical	Nominal Values	Test Method(s)	
Density ( )	0.954 g/cm <sup>3</sup>	ASTM D792	ISO 1183
Melt Flow Rate (190°C/2.16kg)	2 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
Melting Point (DSC)	134°C (273°F)	ASTM D3418	ISO 3146
Freezing Point (DSC)	115°C (239°F)	ASTM D3418	
Vicat Softening Point ( )	127°C (261°F)	ASTM D1525	ISO 306

#### Processing Information

##### General

Maximum Processing Temperature 300°C (572°F)

#### FDA Status Information

Fusabond® E100BR comply with the Code of Federal Regulations, Title 21, Paragraph 175.105, covering the use of adhesive interlayers in composite packages for food use. This regulation describes adhesives that may be safely used as components of articles intended for use in packaging, transporting or holding food. This regulation requires that either (1) the adhesive is separated from the food by a functional barrier, or (2) the quantity of adhesive which contacts fatty or aqueous foods does not exceed the trace amounts at the seams or edges.

Customers should satisfy themselves that the food contact material is serving as a functional barrier to the adhesive.

**Regulatory Information**

For information on regulatory compliance outside the U.S., consult your local DuPont representative.

**Safety & Handling**

As with any hot material, care should be taken to protect the hands and other exposed parts of the body when working with molten polymer.

At temperatures above 300°C (572°F), these resins can evolve low concentrations of fumes. When resins are overheated, more extensive decomposition may occur. Because fumes produced during exposure to high temperatures may be combustible, exposure of overheated resin to atmospheric oxygen should be avoided if possible. Adequate local ventilation should be provided to remove the fumes from the work area.

Disposal of scrap material presents no special problems, and may be accomplished by landfill or by incineration by a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls.

For more detailed information on the safe handling and disposal of these resins, a Product Safety Bulletin and OSHA Material Safety Data Sheets can be obtained from the Regional Office serving you.

**Read and Understand the Material Safety Data Sheet (MSDS) before using this product**

**Regional Centres**

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

**Americas**

DuPont Company, BMP26-2363  
Lancaster Pike & Route 141  
Wilmington, DE 19805 U.S.A.  
Telephone +1 302-774-1161  
Toll-free (USA) 800-628-6208  
Fax +1 302-999-4399

**Asia Pacific**

DuPont China Holding Co., Ltd.  
Shanghai Branch  
399 Keyuan Road, Bldg. 11  
Zhangjiang Hi-Tech Park  
Pudong New District, Shanghai  
P.R. China (Postcode: 201203)  
Telephone +86 21 3862 2888  
Fax +86-21-3862-2889

**Europe / Middle East / Africa**

DuPont de Nemours Int'l. S.A.  
2, Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone +41 22 717 51 11  
Fax +41 22 717 55 00

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Telephone +55 11 4166 8122  
Fax +55 11 4166 8720

<http://fusabond.dupont.com>

*The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.*

*CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.*

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The

*miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.*

*This data sheet is effective as of 01/20/2009 09:01:09 AM and supersedes all previous versions.*