



Kapton®

polyimide film

General Specifications

Introduction

DuPont High Performance Materials manufactures and sells a variety of high-quality plastic film products in conformance with ISO 9002 certification.

These specifications describe the values and tolerances for Kapton® film properties. Where necessary for thorough understanding, test methods and procedures have been included.

Any aspects of the specifications that require further interpretation or clarification should be discussed with representatives of DuPont High Performance Materials.

Types of Kapton® Polyimide Film

DuPont makes several types of Kapton® film. Types HN, FN, and VN are used most commonly.

Types H, F, and V are alternative, special versions of these standard types. The specifications in this bulletin apply to them as well. In addition to these three types of Kapton®, films are available with the following attributes:

- antistat
- thermally conductive
- polyimides for fine line circuitry
- cryogenic insulation
- corona resistant
- pigmented for color
- conformable
- other films tailored to meet customers' needs

Data for these films are covered in separate product bulletins, which can be obtained from your DuPont Kapton® representative.

Type HN Film

Kapton® Type HN is a tough, aromatic polyimide film, exhibiting an excellent balance of physical, chemical, and electrical properties over a wide temperature range, particularly at unusually high temperatures. Chemically, its polyimide polymer makeup is the result of a polycondensation reaction between pyromellitic dianhydride and 4,4'-diaminodiphenyl ether. Kapton® HN is available in the following gauges: 30 (7.5 μm), 50 (12.7 μm), 100 (25.4 μm), 200 (50.8 μm), 300 (76.2 μm), and 500 (127 μm). Other gauges, such as 75 (19.1 μm) and 400 (102 μm), are available by special request.

Type FN Film

Kapton® Type FN film is a heat sealable grade that retains the unique balance of properties of Kapton® Type HN over a wide temperature range. This is achieved by combining Type HN with DuPont Teflon® FEP fluorocarbon resin in a composite structure. **Table 1** lists the common types of FN film available. Other combinations are available. Consult your DuPont Kapton® marketing representative for further information.

Table 2
Mechanical Properties of Kapton® Type HN Polyimide Film

Property	Property Value—Film Thickness, mil (µm)						Method
	0.30 (7.6)	0.50 (12.7)*	1.00 (25.4)*	2.00 (50.8)*	3.00 (76.2)*	5.00 (127)*	
Tensile Strength, psi (MPa) at 23°C (73°F). Machine Direction (MD) and Transverse Direction (TD), min.	16,000 (110)	20,000 (138)	24,000 (165)	24,000 (165)	24,000 (165)	24,000 (165)	ASTM D-882-91, Method A, using an Instron Tensile Tester (specimen size: ½" × 6" [12.7 mm × 152 mm]; jaw separation: 4" [102 mm]; jaw speed: 2"/min [51 mm/min]). Calculate the average of five specimens based on original measured thickness.
Elongation, %, MD and TD, min.	25	35	40	45	50	50	Same as above.
Shrinkage, %, MD and TD at 400°C (752°F), max.	4.0	4.0	2.5	2.5	2.5	2.5	MIL-P-46112B. The percent shrinkage is obtained for either the MD or TD using the average of three measurements in either direction before and after conditioning. Prior to measurement, the 8½" × 11" (216 mm × 279 mm) specimen is conditioned by freely suspending it for 2 hr** in an oven controlled to 400°C (752°F).
Moisture Absorption, %, max.	4.0	4.0	4.0	4.0	4.0	4.0	ASTM D-570-92, using 24-hr immersion at 23°C (73°F). Average of three specimens.

*Also applies to Type VN, except shrinkage, which is shown in Table 5.

**1 hr for 30 and 50 gauge film

Table 3
Electrical Properties of HN Film

Property	Property Value—Film Thickness, mil (µm)						Method
	0.30 (7.6)	0.50 (12.7)*	1.00 (25.4)*	2.00 (50.8)*	3.00 (76.2)*	5.00 (127)*	
Dielectric Strength, AC V/mil (kV/mm), min.	3,000 (118)	3,000 (118)	6,000 (236)	5,000 (197)	4,500 (177)	3,000 (118)	ASTM D-149-94. (Average of ten specimens.) Flat sheets in air placed between ¼" (6 mm) diameter brass electrodes with ⅓₂" (0.8 mm) edge radius subjected to 60 cycles AC voltage at 500 V/sec rate of rise to the breakdown voltage.
Volume Resistivity, ohm-cm at 200°C (392°F), min.	10 ¹²	10 ¹²	10 ¹²	10 ¹²	10 ¹²	10 ¹²	ASTM D-257-93
Dielectric Constant at 1 kHz, max.	4.0	4.0	3.9	3.9	3.9	3.9	ASTM D-150-94. Use conducting silver paint electrodes, two-terminal system of measurement at standard conditions. Results are based on an average of five tests using measured thickness of specimens.
Dissipation Factor at 1 kHz, max.	0.0070	0.0050	0.0036	0.0036	0.0036	0.0036	Same as above.

*Also applies to Type VN

Table 4
Dielectric Strength of Kapton® Type FN
Polyimide Films

Gauge Construction	Minimum Breakdown V/mil (kV/mm)
120FN616	4,200 (165)
120FN616B	4,200 (165)
150FN019	3,700 (146)
200FN919	3,200 (126)
200FN011	3,200 (126)
250FN029	2,750 (108)
300FN021	2,700 (106)
300FN929	2,700 (106)
400FN022	2,200 (87)
500FN131	2,200 (87)

Test Method

Average of ten specimens tested per ASTM D-149-92. Flat sheets in air placed between ¼" (6 mm) diameter brass electrodes with 1/32" (0.8 mm) edge radius subjected to 60 cycles AC voltage. Rise is 500 V/sec to the breakdown voltage.

General

Materials

Kapton® Type HN and Type VN films are polyimide polymers in the form of a film.

Kapton® Type FN film is a combination of Type HN film with Teflon® FEP fluorocarbon resin on one or both sides.

Uniformity

Material shall be uniform in composition and free from defects that impair serviceability and/or appearance in proven applications.

U.S. Cores

Cores shall be of sufficient strength to prevent collapsing from handling. Standard core internal diameters (I.D.) are nominally 3" and 6" (76 mm and 152 mm) with the following specifications:

Paper

3" (76 mm) I.D.	3.032" ± 0.008" (77.01 mm ± 0.2 mm)
6" (152 mm) I.D.	6.028" ± 0.010" (153.11 mm ± 0.25 mm)

Plastic

3" (76 mm) I.D.	3.024" ± 0.005" (76.81 mm ± 0.1 mm)
6" (152 mm) I.D.	6.041" ± 0.010" (153.44 mm ± 0.25 mm)

Core material will be plastic for 3" (76 mm) I.D. cores less than 5/8" (16 mm) wide.

Core material will be fiber for 3" (76 mm) I.D. cores wider than 5/8" (16 mm) and for 6" (152 mm) I.D. cores. A split 3" (76 mm) I.D. fiber core is standard for all universal and Step-Pac™ rolls.

If these cores are not suitable, further information on other options may be obtained from your DuPont Kapton® representative.

Table 5
Shrinkage of Kapton® Type VN Polyimide Film

Property	Property Value Film Thickness, mil (µm)				
	0.50 (12.7)	1.00 (25.4)	2.00 (50.8)	3.00 (76.2)	5.00 (127)
Shrinkage, %, MD and TD at 200°C (392°F), max.	0.10	0.10	0.10	0.10	0.10

Test Method

The percent shrinkage obtained for either the MD or TD by using the average of three measurements in either direction before and after conditioning. Temperature exposure 200°C ± 2°C (392°F ± 3.6°F) for 1 hr. Measurements must be made at the same temperature and humidity conditions before and after conditioning. To ensure sample/ambient equilibrium before and after conditioning, specimens should be exposed for 3 hr.

Width Tolerance

The maximum variation in film width from that specified on the order shall be as follows:

Slit Width Range

1½" (38 mm) or less

1½" to 4" (38 mm to 102 mm)

>4" (>102 mm)

Tolerance

±0.005" (0.13 mm)

±0.030" (0.76 mm)

±0.060" (1.5 mm)

Luxembourg Supply

Cores shall be of sufficient strength to prevent collapsing from handling. Luxembourg supplies pad rolls in widths below 9½" (240 mm) and universal wound rolls.

Standard core internal diameter for Luxembourg is 3" (76 mm) (nominal 3" ±0.008" [76 mm ±0.2 mm]).

Standard cores for pad rolls are paper cores, except for widths below ½" (13 mm), where it will be plastic.

Standard universal: core length

2.8" ±0.08" (70 mm ±2 mm) (split core)

Wide universal: core length

4.3" ±0.08" (110 mm ±2 mm) (non-split core)

A different put-up called Step-Pac™ is available from the U.S. Contact your DuPont Kapton® representative for more information.

Width Tolerance

The maximum variation in film width from that specified on the order shall be as follows:

Slit Width Range

0.9" (22 mm) or less

Universal

6" (152 mm) or less

Pad rolls

6" to 9½" (153 mm to 240 mm)

Pad rolls

Outside diameter tolerance: ±0.4" (10 mm)

Tolerance

0.008" (0.20 mm)

0.016" (0.40 mm)

0.04" (1.00 mm)

Table 6
Kapton® Polyimide Film Specifications and Tolerances

Film Type	Thickness Nominal mil (µm)*	Thickness Tolerance		Width Range		Unit Weight		Area Factor	
		Min. mil (µm)	Max. mil (µm)	Min. in (mm)	Max. in (mm)	Min. g/m ²	Max. g/m ²	ft ² /lb	(m ² /kg)
30HN	0.30 (7.6)	0.24 (6.1)	0.36 (9.1)	¾ (4.8)	52 (1320)	7.6	14.0	453	92.8
50HN	0.50 (12.7)	0.35 (8.9)	0.65 (16.5)	¾ (4.8)	52 (1320)	14.0	26.0	272	55.7
100HN	1.00 (25.4)	0.85 (21.6)	1.15 (29.2)	¾ (4.8)	52 (1320)	32.7	39.7	136	27.9
200HN	2.00 (50.8)	1.75 (44.5)	2.25 (57.2)	¾ (4.8)	52 (1320)	66.9	77.9	68	13.9
300HN	3.00 (76.2)	2.72 (69.1)	3.28 (83.3)	¾ (4.8)	52 (1320)	101.9	115.4	45	9.2
500HN	5.00 (127)	4.65 (118)	5.35 (136)	¾ (4.8)	52 (1320)	169.5	192.5	27	5.5
50VN	0.50 (12.7)	0.35 (8.9)	0.65 (16.5)	¾ (4.8)	52 (1320)	14.0	26.0	272	55.7
100VN	1.00 (25.4)	0.85 (21.6)	1.15 (29.2)	¾ (4.8)	52 (1320)	32.7	39.7	136	27.9
200VN	2.00 (50.8)	1.75 (44.5)	2.25 (57.2)	¾ (4.8)	52 (1320)	66.9	77.9	68	13.9
300VN	3.00 (76.2)	2.72 (69.1)	3.28 (83.3)	¾ (4.8)	50 (1270)	101.9	115.4	45	9.2
500VN	5.00 (127)	4.65 (118)	5.35 (136)	¾ (4.8)	50 (1270)	169.5	192.5	27	5.5
120FN616	1.20 (30.5)	1.10 (27.9)	1.40 (35.6)	¾ (4.8)	44 (1118)	41.0	58.0	104	21.3
120FN616B	1.30 (33.0)	1.20 (30.5)	1.50 (38.1)	¾ (4.8)	44 (1118)	47.0	54.0	92	18.8
150FN019	1.50 (38.1)	1.25 (31.8)	1.75 (44.5)	¾ (4.8)	44 (1118)	53.0	74.0	77	15.8
200FN011	2.00 (50.8)	1.70 (43.2)	2.30 (58.4)	¾ (4.8)	44 (1118)	77.0	104.0	54	11.1
200FN919	2.00 (50.8)	1.70 (43.2)	2.30 (58.4)	¾ (4.8)	44 (1118)	77.0	104.0	54	11.1
250FN029	2.50 (63.5)	2.25 (57.2)	2.75 (69.9)	¾ (4.8)	44 (1118)	87.0	113.0	49	10.0
300FN021	3.00 (76.2)	2.60 (66.0)	3.40 (86.4)	¾ (4.8)	44 (1118)	111.0	142.0	39	8.0
300FN929	3.00 (76.2)	2.60 (66.0)	3.40 (86.4)	¾ (4.8)	44 (1118)	111.0	142.0	39	8.0
400FN022	4.00 (102)	3.50 (88.9)	4.50 (114)	¾ (4.8)	44 (1118)	163.0	200.0	27	5.5
500FN131	5.00 (127)	4.50 (114)	5.50 (140)	¾ (4.8)	44 (1118)	195.0	239.0	23	4.7

*Reference: ASTM D-374-94, Method A, C, or D.

The usual dimensions of pad rolls are 3" (76 mm) I.D. × 6" (152 mm) or 9" (230 mm) outside diameter (O.D.) for widths up to 4" (102 mm). In Luxembourg, 152 mm, 180 mm, 203 mm, and 240 mm O.D. rolls are available. For wider rolls, the usual dimensions are 6" (152 mm) I.D. × 9½" (240 mm) or 11" (280 mm) O.D. For Universal and Step-Pac™ rolls, the dimensions are 3" (76 mm) I.D. × 6" (152 mm), 8" (203 mm), or 12" (305 mm) O.D. If these dimensions are not suitable, information on other options is available from your DuPont High Performance Films technical or customer service representative.

Roll Types

Kapton® polyimide film is supplied in three types of rolls: pad, universal, and Step-Pac™ wind.

Pad Roll Specifications

- Core width will be the film width $+1/8''$ (+3.2 mm), -0.
- Core edges shall not project more than $1/16''$ (1.6 mm) beyond the roll face on either side.
- Core shall not be recessed on either side.
- The outside and starting ends of the film shall be fastened in a manner to prevent unwinding.
- “Dishing” or “cupping” may not exceed $1/16''$ (1.6 mm), measured with a straightedge across the diameter of the roll.

Universal and Step-Pac™ Roll Specifications

- The difference between the lengths of the projecting core on each side shall not exceed $3/16''$ (4.8 mm).
- Film shall not project from the main body of the roll more than $1/8''$ (3.2 mm).
- The outside and starting ends of the film shall be fastened in a manner to prevent unwinding.
- Roll face depression, the difference between the highest and lowest points of the roll, unstressed, shall not exceed $3/16''$ (4.8 mm).

Table 7
Reference Guide: Standard Length versus Roll O.D. (U.S. Supply)

Type	Standard Length Roll	Roll O.D.	
		3" Core I.D.	6" Core I.D.
100HN	5,000 ft (1,525 m)	9½" (241 mm)	11" (279 mm)
	10,000 ft (3,050 m)	11" (279 mm)	14" (356 mm)
200HN	2,500 ft (763 m)	9½" (241 mm)	11" (279 mm)
300HN	1,670 ft (509 m)	9½" (241 mm)	11" (279 mm)
500HN	1,000 ft (305 m)	9½" (241 mm)	11" (279 mm)

Splices

Description

Three types of splice are available.

- Mylar® polyester film-based yellow tape (standard).
- Kapton® polyimide film-based tape (special requirements only).
- Heat seal splice, 12" (305 mm) or less in width (Type FN).

Splices will be centered on the joint to $\pm 1/4''$ (± 6 mm). They will be smooth and wrinkle-free to avoid distortion of the adjacent film layers in the roll.

Tape Splices

Tape splices are standard on all gauges of HN and VN film and on all gauges of FN film more than 12" (305 mm) wide.

Tape splices are made with the butt edges of the film covered on both sides with pressure-sensitive adhesive tape. Two-inch (50 mm) wide splicing tape is used.

Heat Seal Splices

Overlap heat seal splices are made on all FN films, except 250FN029, with an overlap that is a minimum of $3/8''$ (9.5 mm) wide.

On 250FN029, a butt splice is made using 120FN616 as the joining tape applied on the FEP surface. The butt splice is oriented with the 120FN616 tape on the top of the film as it unwinds from a universal put-up and on the bottom as it unwinds from a pad.

Overlap heat seal splices for one-side and two-side FEP composites are oriented with the leading edge of the new film on the bottom for universal and Step-Pac™ put-ups. Pad put-ups of one- or two-side FEP composites have the leading edge of the new film on the top.

Packaging and Marking

Packaging

Kapton® polyimide film shall be adequately packed to prevent loss of contents or damage during shipment.

All film will be wrapped with a non-fibrous material.

Marking

Kapton® is identified, as shown in **Table 8**, to allow complete traceability back to the raw materials and processing conditions.

Arrangements for special markings can be made (such as part or specification number). Consult with your DuPont Kapton® technical or customer service representative for details.

All package marking information is available with bar code labels.

Table 8
Package Marking

	Shipping Container	Package	Core Label*
Scheduled Date	X	X	X
Customer Order Number	X	X	
DuPont Order Number	X	X	X
Gauge	X	X	X
Type	X	X	X
Width	X	X	X
Number of Rolls per Container	X	X	
Net Weight	X	X	
Actual Footage			X
Mill Roll Number	X	X	X
I.D. and O.D.**	X	X	

* Affixed to the core on all cores. 2.25" (57 mm) wide and over.

Included with the package on all cores less than 2.25" (57 mm) wide

** Inside diameter of core and nominal outside diameter of roll

North America

United States

DuPont High Performance Materials
P.O. Box 89
Route 23 South and DuPont Road
Circleville, OH 43113
Ordering Information:
Tel: (800) 967-5607
Product Information:
Tel: (800) 237-4357
Fax: (800) 879-4481

Canada

DuPont Canada, Inc.
P.O. Box 2200, Streetsville
Mississauga, Ontario, Canada
L5M 2H3
Inquiries: (905) 821-5603
Customer Service: (800) 784-5231
Fax: (905) 821-5230

Latin America

Argentina

DuPont Argentina
Av. Mitre y Calle 5
CP 1884, Berazategui, Argentina
Pcia de Buenos Aires
Tel: 54-1-256-2435
Fax: 54-1-319-4451

Brazil

DuPont do Brasil
Al. Itapecuru, 506
06454-080, Alphaville
Barueri, Sao Paulo
Tel: 55-11-421-8689
Fax: 55-11-421-8686

Mexico

DuPont S.A. de C.V.
Homero 206
Col. Chapultepec Morales
Mexico, D.F. 11570
Tel: 525-722-1184
Fax: 525-722-1370

Venezuela

DuPont Venezuela
Edificio "Los Frailes"
Calle la Guarita
Urbanization Chuao
CP 1060, Caracas, Venezuela
Tel: 58-2-92-8547
Fax: 58-2-91-5638

Europe

Luxembourg

DuPont de Nemours
(Luxembourg) S.A.
Contern
L-2984 Luxembourg
Grand Duchy of Luxembourg
Tel: 352-3666-5575
Fax: 352-3666-5000

Community of Independent States

DuPont de Nemours Intl. S.A.
Representative Office—Corporate
B. Palashevsky per. 13/2
103104 Moscow
Russia
Tel: 7-095-956-3850
Fax: 7-095-956-3853

Deutschland

DuPont de Nemours (Deutschland)
GmbH
DuPont Straße 1
D-61343 Bad Homburg v.d.H.
Tel: 49-6172-87-2790
Fax: 49-6172-87-2930

France

DuPont de Nemours (France) S.A.
Z.A. de Courtaboeuf
3 Av. du Canada—B.P. 85
F-91943 Les Ulis Cedex A
Tel: 33-1-69 82 52 96
Fax: 33-1-69-82 53 92

Italy

DuPont de Nemours (Italiana) S.p.A.
16, Via A. Volta
I-20093 Cologno Monzese
Tel: 39-2-25-302 326
Fax: 39-2-25-43310

United Kingdom

DuPont (U.K.) Ltd.
Maylands Avenue
GB-Hemel Hempstead
Herts HP2 7DP
Tel: 44-1442-21-8637
Fax: 44-1442-21-8639

Asia Pacific

Japan

DuPont Kabushiki Katsha
Arco Tower
8-1, Shimomeguro 1-chome
Meguro-ku, Tokyo 153
Japan
Tel: 81-3-5434-6139
Fax: 81-3-5434-6193

Hong Kong/China

DuPont China Ltd.
1122 New World Office Bldg.
East Wing
Salisbury Road, Kowloon
Hong Kong
Tel: 852-2734-5401
Fax: 852-2721-4117

India

DuPont South Asia Ltd.
503-505, Madhava
Bandra Kurla Commercial Complex
Bandra (E)
Bombay 400 051
India
Tel: 91-22-6438255
Fax: 91-22-6438297

Korea

DuPont Korea Ltd.
4/5th Floor, Asia Tower
#726, Yeoksam-dong, Kangnam-ku
Seoul 135-082, Korea
Tel: 82-2-222-5398
Fax: 82-2-222-5476

Singapore

DuPont Singapore Pte Ltd.
1 Maritime Square
#07-01 World Trade Centre
Singapore 099253
Tel: 65-279-3434
Fax: 65-279-3456

Taiwan

DuPont Taiwan Ltd.
7, Tsu-Chiang 1st Road
Chungli, Taoyuan
Taiwan, ROC
Tel: 866-3-4549204
Fax: 866-3-4620676

Contact DuPont on the Internet at www.dupont.com

The information given herein is based on data believed to be reliable, but DuPont makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.



Kapton[®]
polyimide film