

DuPont™ TraSys® 423

Mandrel Release Coating

Description

TraSys® 423 mandrel release coating is a water-based dispersion designed for water stripping operations and can be applied to flexible or rigid mandrels. When applied to a mandrel, it exhibits outstanding release or antistick properties and has a very low coefficient of friction. It is clean, nonoily, nonstaining, chemically inert, and can function in temperatures to 260°C (500°F) or higher.

Uses

TraSys® 423 mandrel release coating has unique properties, making it an excellent release agent for all types of rubber, fluoropolymer, and plastic. Unlike oily release agents, when properly applied, it does not cause hose tube pitting.

Directions for Use

TraSys® 423 mandrel release coating should be applied to clean, dry surfaces. The following are suggested methods of application.

- **Dipping or Flooding**—The easiest and most widely used method for applying TraSys® 423 mandrel release coating. A wiper system should be used to strip off excess amounts, ensuring a thin, even coating over the entire length of the mandrel.
- **Spraying**—Particularly effective in depositing a very thin coating with excellent adhesion. This system can be used with a hand spray gun or with automatic spray heads, which can be operated intermittently or continuously.
- **Wiping or Brushing**—Very effective for coating small amounts of mandrels or selected areas on a mandrel.

Regardless of method of application, the coating must be dried completely before use.

Typical Properties

Primary Polymer: Fluorochemical
Specific Gravity: 1.0
Odor: Slight
Color: White
Flash Point: None

Storage and Handling

Contact with the skin should be avoided. Adequate ventilation must be provided in work areas. Breathing vapors should be avoided. If spraying, care should be taken to avoid inhaling mist or vapors, just as sprayed paint inhalation should be avoided.

Vapor may develop slight pressure. Therefore, care should be exercised when opening containers. Containers should be closed promptly after removing part of the contents to avoid evaporation.

If this product is exposed to extreme heat conditions from misuse or equipment failure, toxic decomposition products that include hydrogen fluoride can occur. Hydrogen fluoride has an ACGIH threshold limit value of 3 parts per million parts of air as a ceiling limit, an OSHA permissible exposure limit (PEL) of 3 ppm of fluoride as an 8-hr time-weighted average, and 6 ppm of fluoride as a short-term exposure limit (STEL).

Always wash hands after handling TraSys® 423 release coating.

Do not smoke while handling this product.

Shelf Life

TraSys® 423 has a shelf life of 1 year from the date of shipment.



The miracles of science™

Packaging

TraSys® 423 is available in 1-, 5-, and 55-gal containers. Larger volume orders may be packaged in specialty containers.

Shipping Limitations

None

For more information or technical assistance, call: (800) 441-9503
or visit us on the Web: www.dupont.com/releasesystems

Or call the Coating & Release Systems hotline in the **United States** at (800) 441-9503,
E-mail: release.systems@usa.dupont.com
Canada at 800-263-5924, E-mail: products@can.dupont.com
Europe, Mideast, and Africa at +32.3.543.1267, E-mail: lubricants@lux.dupont.com
Asia/Pacific—including India at 886-2-2514-4434, E-mail: release.systems@usa.dupont.com
Mexico and Central America at +011-52-55-5722-1150, E-mail: ceac@mex.dupont.comx
South America—all Countries at 55-11-4166-8601, E-mail: produtos.brasil@bra.dupont.com

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

The DuPont oval logo, DuPont™, The miracles of science™ and TraSys® are trademarks or registered trademarks of DuPont.
Copyright © 2004 E.I. du Pont de Nemours and Company. All rights reserved.



The miracles of science™