

DuPont™ Krytox® XHT-AC and XHT-ACX

Performance Lubricants

This grease is a special high temperature grease with low oil evaporation that provides antiwear and rusting protection and is compatible with all elastomers and plastics. It has excellent lubrication over a broad temperature range but is designed to work best at temperatures over 200°C (400°F). It is nonflammable, oxygen-compatible, and chemically inert. Krytox® provides extended lubrication intervals and longer equipment life.

Typical Properties of XHT-AC Series PFPE Grease

	XHT-AC	XHT-ACX
Estimated Useful Range		
°C	-20/300	-10/300
°F	-4/572	14/572
Base Oil Viscosity, cSt		
20°C (68°F)	1,830	2,560
40°C (104°F)	500	738
100°C (212°F)	47	65
Oil Viscosity Index	149	158
Oil Pour Point		
°C	-25	-15
°F	-13	5
Antirust Rating, ASTM D-1743	Pass	Pass
Maximum Volatility, % in 22 hr 204°C (400°F)	<1	<0.75
Appearance	White, creamy consistency	White, creamy consistency
Specific Gravity, 0°C (32°F)	1.99	1.99

This grease is an extension of the GPL 22X series but is designed to give higher performance in the 204–302°C (400–575°F) ranges. It should be used below 320°C (608°F), where the PTFE thickener could begin to melt. The base oil is an extremely viscous oil that provides good viscosity and lower evaporation at high temperatures.

Typical applications include: paint plant conveyor bearings, corrugator and paper machine bearings, aluminum can manufacturing bearings, welding machines, high temperature fans, textile equipment, tenter frames, high temperature ovens, conveyor systems in glass and aluminum plants, textile calendar roll bearings, brick kiln car bearings, valve lubrication, ventilation fan bearing grease, and rod mills.

Applications for these lubricants are generally of a critical nature where temperatures are reaching extremes that conventional lubricants cannot handle, and they are expected to be durable in the most aggressive environments. Where failure of components is not an option whether because of durability, warranty, safety, loss of productivity or downtime, Krytox® is the lubricant of choice in a wide range of industries and applications.

Grease is made to a standard NLGI grade 2. PTFE is the standard thickener.

XHT-AC was also called GPL 227-500 when it was first developed.


XHT-ACX was also called LVP-228 when it was first developed.



The miracles of science™

Krytox® PFPE Oils and Greases

Krytox® PFPE oils are clear, colorless, fluorinated synthetic oils that are nonreactive, nonflammable, safe in chemical and oxygen service, and are long lasting. Krytox® is a perfluoropolyether (PFPE)—also called perfluoroalkylether (PFAE) or perfluoropolyalkylether (PFPAE) with the following chemical structure:



The polymer chain is completely saturated and contains only carbon, oxygen, and fluorine. On a weight basis, a typical Krytox® oil contains 21.6% carbon, 9.4% oxygen, and 69.0% fluorine.

Compatibility with Metals

Because of their low surface tensions, Krytox® lubricants easily wet metallic surfaces. Krytox® lubricants are chemically inert and, therefore, have no adverse effect on metals when the temperature is below 288°C (550°F). Above 288°C (550°F), many alloy steels, stainless steels, and other metals such as aluminum alloy, titanium alloy, nickel alloy, and cobalt alloy can be used with Krytox®.

For more information or technical assistance, call: (800) 424-7502
or visit us on the Web: <http://www.krytox.com>

Or call the Krytox® hotline in the **United States** at (800) 424-7502, E-mail: krytox@usa.dupont.com
Canada at 800-263-5924, E-mail: products@can.dupont.com
Europe, Mideast, and Africa at +32.3.543.1267, E-mail: lubricants@lux.dupont.com
Asia/Pacific—Including India at 886-2-2514-4434, E-mail: krytox.lubricants@twn.dupont.com
Mexico and Central America at +52-5-722-1150, www.dupont.com.mx
South America—All Countries at 55-11-4166-8601, E-mail: produtos.brasil@bra.dupont.com

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

Copyright © 2001 E.I. du Pont de Nemours and Company. All rights reserved.

