

DuPont™ Krytox® XHT-AC and XHT-ACX

PERFORMANCE LUBRICANTS

Product Data Sheet

This grease is a special high temperature grease with low oil evaporation that provides antiwear and rusting protection and is compatible with all elastomers and plastics. It has excellent lubrication over a broad temperature range, but is designed to work best at temperatures over 200°C (400°F). It is nonflammable, oxygen-compatible, and chemically inert. DuPont™ Krytox® greases provide extended lubrication intervals and longer equipment life.

Typical Properties of Krytox® XHT-AC Series PFPE Grease

	XHT-AC	XHT-ACX
Estimated Useful Range		
°C	-20/300	-10/300
°F	-4/572	14/572
Base Oil Viscosity, cSt		
20°C (68°F)	1,712	2,610
40°C (104°F)	500	738
100°C (212°F)	47	65
Oil Viscosity Index	149	158
Oil Pour Point		
°C	-25	-15
°F	-13	5
Antirust Rating, ASTM D-1743	Pass	Pass
Maximum Volatility in 22 hr, %		
204°C (400°F)	<1	<0.75
Appearance	White, creamy consistency	White, creamy consistency
Specific Gravity at 0°C (32°F)	1.99	1.99

This grease is an extension of the 240 series and GPL 22X series but is designed to give higher performance in the 204–302°C (400–575°F) ranges. It should be used below 320°C (608°F), where the PTFE thickener could begin to melt. The base oil is an extremely viscous oil that provides good viscosity and lower evaporation at high temperatures.

Typical applications include: paint plant conveyor bearings, corrugator and paper machine bearings, aluminum can manufacturing bearings, welding machines, high temperature fans, textile equipment, tenter frames, high temperature ovens, conveyor systems in glass and aluminum plants, textile calendar roll bearings, brick kiln car bearings, valve lubrication, ventilation fan bearing grease, and rod mills.

Applications for these lubricants are generally of a critical nature where temperatures are reaching extremes that conventional lubricants cannot handle. Lubricants are expected to be durable in the most aggressive environments. Where failure of components is not an option whether because of durability, warranty, safety, loss of productivity or downtime, Krytox® is the lubricant of choice in a wide range of industries and applications.


Grease is made to a standard NLGI grade 2. PTFE is the standard thickener.



The miracles of science™

DuPont™ Krytox® PFPE Oils and Greases

Krytox® PFPE oils are clear, colorless, fluorinated synthetic oils that are nonreactive, nonflammable, safe in chemical and oxygen service, and are long lasting. Krytox® is a perfluoropolyether (PFPE)—also called perfluoroalkylether (PFAE) or perfluoropolyalkylether (PFPAE) with the following chemical structure:



where n = 10 to 60

The polymer chain is completely saturated and contains only carbon, oxygen, and fluorine. On a weight basis, a typical Krytox® oil contains 21.6% carbon, 9.4% oxygen, and 69.0% fluorine.

Compatibility with Metals

Because of their low surface tensions, Krytox® lubricants easily wet metallic surfaces. Krytox® lubricants are chemically inert and, therefore, have no adverse effect on metals when the temperature is below 288°C (550°F). Above 288°C (550°F), many alloy steels, stainless steels, and other metals such as aluminum alloy, titanium alloy, nickel alloy, and cobalt alloy can be used with Krytox® lubricants.

For more information or for technical assistance, please call us at 1-800-424-7502 or contact us at krytox@usa.dupont.com.

For international sales and support contacts, visit us at www.lubricants.dupont.com

Copyright © 2008 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™ and Krytox® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

H-91814-2 (07/08) Printed in the U.S.A.

The information set forth herein is furnished free of charge and based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.



The miracles of science™