



# Suva<sup>®</sup> refrigerants

Only by DuPont


## VELOCITY IN LINES for HP80 REFRIGERANT (20°C Evaporator Outlet) SI Units

### Dimensions of Type L Copper Tubing

Outside Diameter Inches	Inside Diameter	
	Inches	mm
6-1/8	5.845	148.5
5-1/8	4.875	123.8
4-1/8	3.905	99.2
3-5/8	3.425	87.0
3-1/8	2.945	74.8
2-5/8	2.465	62.6
2-1/8	1.985	50.4
1-5/8	1.505	38.2
1-3/8	1.265	32.1
1-1/8	1.025	26.0
7/8	0.785	19.9
3/4	0.666	16.9
5/8	0.545	13.8
1/2	0.430	10.9
3/8	0.315	8.0

DuPont Fluorochemicals  
Wilmington, Delaware 19898

# HP80 REFRIGERANT VELOCITY IN LINES (20°C Evap. Outlet)



**For Sales Information:**

**DuPont Fluorochemicals  
Customer Service Center, B-15305  
Wilmington, DE 19898/U.S.A.  
(302) 774-2099  
1-800-441-9442**

**For Technical Information:**

**Fluorochemicals Laboratory  
Wilmington, DE/U.S.A.  
(302) 999-3129  
1-800-582-5606**

**Europe**

DuPont de Nemours  
International S.A.  
2 Chemin du Pavillon  
P.O. Box 50  
CH-1218 Le Grand-Saconnex  
Geneva, Switzerland  
41-22-717-5111

**Canada**

DuPont Canada, Inc.  
P.O. Box 2200, Streetsville  
Mississauga, Ontario  
L5M 2H3  
(416) 821-3300

**Mexico**

DuPont, S.A. de C.V.  
Homero 206  
Col. Chapultepec Morales  
C.P. 11570 Mexico, D.F.  
52-5-250-8000

**South America**

DuPont do Brasil S.A.  
Alameda Itapicuru, 506  
Alphaville 06400 Barueri  
Sao Paulo, Brazil  
55-11-421-8509

DuPont Argentina S.A.  
Casilla Correo 1888  
Correo Central  
1000 Buenos Aires, Argentina  
54-1-311-8167

**Pacific**

DuPont Australia  
P.O. Box 930  
North Sydney, NSW 2060  
Australia  
61-2-923-6165

**Japan**

Mitsui DuPont Fluorochemicals  
Company, Ltd.  
Mitsui Seimei Building  
2-3, 1-Chome Ohtemachi  
Chiyoda-Ku, Tokyo 100 Japan  
81-3-3216-8451

**Asia**

DuPont Taiwan  
P.O. Box 81-777  
Taipei, Taiwan  
886-2-514-4400

DuPont Asia Pacific Limited  
P.O. Box TST 98851  
Tsim Sha Tsui  
Kowloon, Hong Kong  
852-734-5345

DuPont Thailand  
P.O. Box 2398  
Bangkok 10501, Thailand  
66-2-238-4361

DuPont China Ltd.  
Room 1704, Union Bldg.  
100 Yanan Rd. East  
Shanghai, PR China 200 002  
Phone: 86-21-328-3738  
Telex: 33448 DCLSH CN  
Fax: 86-21-320-2304

DuPont Far East Inc.  
P.O. Box 12396  
50776 Kuala Lumpur, Malaysia  
Phone: 60-3-232-3522  
Telex: (784) 30391 DUFE M  
Fax: 60-3-238-7250

DuPont Korea Ltd.  
C.P.O. Box 5972  
Seoul, Korea  
82-2-721-5114

DuPont Singapore Pte. Ltd.  
1 Maritime Square #07 01  
World Trade Centre  
Singapore 0409  
65-273-2244

DuPont Far East, Philippines  
5th Floor, Solid Bank Building  
777 Paseo de Roxas  
Makati, Metro Manila  
Philippines  
63-2-818-9911

DuPont Far East Inc.  
7A Murray's Gate Road  
Alwarpet  
Madras, 600 018 India  
91-44-454-029

DuPont Far East Inc.-  
Pakistan  
9 Khayaban-E-Shaheen  
Defence Phase 5  
Karachi, Pakistan  
92-21-533-350

DuPont Far East Inc.  
P.O. Box 2553/Jkt  
Jakarta 10001  
Indonesia  
62-21-517-800

The information contained herein is based on technical data and tests which we believe to be reliable and is intended for use by persons having technical skill, at their own discretion and risk. Since conditions of use are outside of DuPont's control, we can assume no liability for results obtained or damages incurred through the application of the data presented.

