

DuPont™ RoofLiner with Elvaloy®

PHYSICAL PROPERTIES DATA SHEET

PROPERTIES	METHOD	VALUE
Water Penetration Resistance	AATCC 127	> 394 inches > 1,000 cm
Liquid Water Transmission	ASTM D 4869 (Section 8.3)	PASS
Basis Weight	TAPPI T 410	6.2 oz/yd ²
Breaking Strength	ASTM D 1682 (MD) (CD)	150 lb _f 95 lb _f
Pliability	ASTM D 226 (Table 1)	PASS
Accelerated Aging	AC48 (Section 4.7)	PASS
Ultra Violet Exposure (LAB)	AC48 (Section 4.8)	PASS
Ultra Violet Exposure (Field)	ASTM G90 (EMMAQUA TUV)	180 days (6 months)
Surface Burning Characteristics	ASTM E84	
	Flame Spread Index	0
	Smoke Developed Index	30

For more information about DuPont™ RoofLiner with Elvaloy®, please call 1-800-448-9835 or visit us at www.Roofing.DuPont.com



The miracles of science™

DuPont™
RoofLiner
with Elvaloy®