

## DuPont™ Surlyn® 9721

### Surlyn® resins Product Data Sheet

#### Description

**Product Description** Surlyn® 9721 is a zinc ionomer thermoplastic resin. It is available for use in conventional extrusion and injection equipment, to create various sheets or shapes.

Surlyn® 9721 thermoplastic resin is an advanced ethylene/methacrylic acid (E/MAA) copolymer, in which the MAA acid groups have been partially neutralized with zinc ions.

#### Restrictions

**Material Status** • Commercial: Active

#### Typical Characteristics

**Features** Zinc Ionomer

**Characteristics / Benefits**

- Embrittlement Temperature ----- (-110C) ----- ASTM D746
- Abrasion Resistance ----- 410 NBS Index ----- ASTM D1630
- Flexural Modulus (23C) ----- 250 MPa ----- ASTM D790
- Flexural Modulus (-20C) ----- 717 MPa ----- ASTM D790
- Tensile Elongation @ Break (23C) ---- 440% ----- ASTM D638 / ISO 527-2
- Tensile Strength @ Break (23C) ----- 10.3 MPa ----- ASTM D638 / ISO 527-2
- Tensile Strength @ Yield (23C) ----- 11.7 MPa ----- ASTM D638
- Tensile Impact Strength (23C) ----- 600 ft-lb/in2 ----- ASTM D1822
- Tensile Impact Strength (-40C) ----- 495 ft-lb/in2 ----- ASTM D1822
- Hardness (Shore D) ----- 61 ----- ASTM D2240 / ISO 868
- Haze (0.25 inch) ----- 12% ----- ASTM D1003
- Tear Strength (23C) ----- 1.02 kN/m ----- ASTM D624

**Applications** Injection Molding / Sheet Extrusion / Blow Molding

#### Typical Properties

Physical	Nominal Values	Test Method(s)	
Density ( )	0.96 g/cm <sup>3</sup>	ASTM D792	ISO 1183
Melt Flow Rate (190°C/2.16kg)	1 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
Melting Point (DSC)	92°C (198°F)	ASTM D3418	ISO 3146
Freezing Point (DSC)	76°C (169°F)	ASTM D3418	
Vicat Softening Point ( )	71°C (160°F)	ASTM D1525	ISO 306

#### Processing Information

## General

Maximum Processing Temperature 285°C (545°F)

General Processing Information Surlyn® 9721 is normally processed at melt temperatures ranging from 185°-285°C (365°-545°F). Actual processing temperatures will usually be determined by either the specific equipment or substrate or one of the other polymers in a coextrusion or coinjection..

Materials of construction used in the processing of this resin should be corrosion resistant. Stainless steels of the types 316, 15-5PH, and 17-4PH are excellent, as is quality chrome or nickel plating, and in particular duplex chrome plating. Type 410 stainless steel is satisfactory, but needs to be tempered at a minimum temperature of 600°C (1112°F) to avoid hydrogen-assisted stress corrosion cracking. Alloy steels such as 4140 are borderline in performance. Carbon steels are not satisfactory. While stainless steels can provide adequate corrosion protection, in some cases severe purging difficulties have been encountered. Nickel plating has been satisfactory, but experiments have shown that chrome surfaces have the least adhesion to acid based polymers. In recent years, the quality of chrome plating has been deteriorating due to environmental pressures, and the corrosion protection has not always been adequate. Chrome over top of stainless steel seems to provide the best combination for corrosion protection and ease of purging.

If surface properties of the extruded resin require modification (such as, lower C.o.F. for packaging machine processing), refer to the Conpol™ Processing Additive Resins product information guide.

After processing Surlyn, purge the material out using a polyethylene resin, preferably with a lower melt flow rate than the Surlyn resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your DuPont Sales Representative.

Never shut down the extrusion system with Surlyn in the extruder and die. Properly purge out the Surlyn with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

## FDA Status Information

Surlyn® 9721 resin complies with the provisions of U.S. Food and Drug Administration (FDA) Title 21 Code of Regulations 177:1330.

## Safety & Handling

Surlyn® 9721 as supplied by DuPont are not considered hazardous materials. As with any hot material, care should be taken to protect the hands and other exposed parts of the body when handling molten polymer. At recommended processing temperatures, small amounts of fumes may evolve from the resins. When resins are overheated, more extensive decomposition may occur. Adequate ventilation should be provided to remove fumes from the work area. Disposal of scrap presents no special problems and can be by landfill or incineration in a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls. For more detailed information on the safe handling and disposal of DuPont resins, a Material Safety Data Sheet can be obtained from the DuPont Packaging and Industrial Polymers website or by contacting your sales representative.

**Read and Understand the Material Safety Data Sheet (MSDS) before using this product**

## Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

**Americas**

**Asia Pacific**

**Europe / Middle East / Africa**

DuPont Company, BMP26-2363  
Lancaster Pike & Route 141  
Wilmington, DE 19805 U.S.A.  
Telephone +1 302-774-1161  
Toll-free (USA) 800-628-6208  
Fax +1 302-999-4399

DuPont China Holding Co., Ltd.  
Shanghai Branch  
399 Keyuan Road, Bldg. 11  
Zhangjiang Hi-Tech Park  
Pudong New District, Shanghai  
P.R. China (Postcode: 201203)  
Telephone +86 21 3862 2888  
Fax +86-21-3862-2889

DuPont de Nemours Int'l. S.A.  
2,Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone +41 22 717 51 11  
Fax +41 22 717 55 00

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Telephone +55 11 4166 8122  
Fax +55 11 4166 8720

<http://surlyn.dupont.com>

*The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.*

*CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.*

*Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.*

*This data sheet is effective as of 08/14/2009 03:29:33 PM and supersedes all previous versions.*