

DuPont™ Surlyn® 1652-1

Surlyn® resins Product Data Sheet

**Description**

Product Description	Surlyn® 1652-1 is available for use in conventional blown, cast film, sheet extrusion and coextrusion equipment. It is also used in extrusion coating and coextrusion coating equipment designed to process polyethylene and ethylene copolymer type resins.
---------------------	--

**Restrictions**

Material Status	<ul style="list-style-type: none"> <li>• Commercial: Active</li> </ul>
-----------------	--

**Typical Characteristics**

Features	Zinc Ionomer
----------	--------------

**Typical Properties**

Physical	Nominal Values	Test Method(s)	
Density ( )	0.94 g/cm <sup>3</sup>	ASTM D792	ISO 1183
Melt Flow Rate (190°C/2.16kg)	4.5 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
Melting Point (DSC)	100°C (212°F)	ASTM D3417	ISO 3146
Freezing Point (DSC)	80°C (176°F)	ASTM D3417	
Vicat Softening Point ( )	79°C (174°F)	ASTM D1525	ISO 306

**Processing Information**

**General**

Maximum Processing Temperature	300°C (572°F)
General Processing Information	Surlyn® 1652-1 is normally processed at melt temperatures ranging from 185°-285°C (365°-545°F) in flat die equipment. For cast film / sheet, a typical extruder profile is below. Actual processing temperatures will usually be determined by either the specific equipment or substrate or one of the other polymers in a coextrusion.

Materials of construction used in the processing of this resin should be corrosion resistant. Stainless steels of the types 316, 15-5PH, and 17-4PH are excellent, as is quality chrome or nickel plating, and in particular duplex chrome plating. Type 410 stainless steel is satisfactory, but needs to be tempered at a minimum temperature of 600°C (1112°F) to avoid hydrogen-assisted stress corrosion cracking. Alloy steels such as 4140 are borderline in performance. Carbon steels are not satisfactory. While stainless steels can provide adequate corrosion protection, in some cases severe purging difficulties have been encountered. Nickel plating has been satisfactory, but experiments have shown that chrome surfaces have the least adhesion to acid based polymers. In recent years, the quality of

chrome plating has been deteriorating due to environmental pressures, and the corrosion protection has not always been adequate. Chrome over top of stainless steel seems to provide the best combination for corrosion protection and ease of purging.

If surface properties of the extruded resin require modification (such as, lower C.o.F. for packaging machine processing), refer to the Conpol™ Processing Additive Resins product information guide.

After processing Surlyn®, purge the material out using a polyethylene resin, preferably with a lower melt flow rate than the Surlyn® resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your DuPont Sales Representative.

Never shut down the extrusion system with Surlyn® in the extruder and die. Properly purge out the Surlyn® with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

<b>Blown Film Processing</b>	<b>Nominal Values</b>
Blown Film Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	135°C (275°F)
Second Zone	160°C (320°F)
Third Zone	185°C (365°F)
Fourth Zone	185°C (365°F)
Fifth Zone	185°C (365°F)
Adapter Zone	185°C (365°F)
Die Zone	185°C (365°F)
<b>Cast Film / Sheet Processing</b>	<b>Nominal Values</b>
Cast Film Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	160°C (320°F)
Second Zone	210°C (410°F)
Third Zone	235°C (455°F)
Fourth Zone	235°C (455°F)
Fifth Zone	235°C (455°F)
Adapter Zone	235°C (455°F)
Die Zone	235°C (455°F)
<b>Extrusion Coating/Lamination Processing</b>	<b>Nominal Values</b>
Extrusion Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	160°C (320°F)
Second Zone	210°C (410°F)
Third Zone	260°C (500°F)
Fourth Zone	285°C (545°F)
Fifth Zone	285°C (545°F)
Adapter Zone	285°C (545°F)
Die Zone	285°C (545°F)

**FDA Status Information**

Surlyn® 1652-1 conforms to the United States Code of Federal Regulations, Title 21, Paragraph 177.1330 covering its use as a food contact surface subject to the extractives limitations on the finished food contact article as described in the regulation.

**Regulatory Information**

For information on regulatory compliance outside of the U.S., consult your local DuPont representative.

**Safety & Handling**

Surlyn® 1652-1 as supplied by DuPont are not considered hazardous materials. As with any hot material, care should be taken to protect the hands and other exposed parts of the body when handling molten polymer. At recommended processing temperatures, small amounts of fumes may evolve from the resins. When resins are overheated, more extensive decomposition may occur. Adequate ventilation should be provided to remove fumes from the work area. Disposal of scrap presents no special problems and can be by landfill or incineration in a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls. For more detailed information on the safe handling and disposal of DuPont resins, a Material Safety Data Sheet can be obtained from the DuPont Packaging and Industrial Polymers website or by contacting your sales representative.

---

**Read and Understand the Material Safety Data Sheet (MSDS) before using this product**

---

---

**DuPont Offices Worldwide**

---

**Americas**

DuPont Company  
Barley Mill Plaza 26-2363  
Lancaster Pike & Route 141  
Wilmington, DE 19880-0026 U.S.A.  
Telephone +1 302-774-1161  
Toll-free (USA) 800-628-6208 prompt "6"  
Fax +1 302-999-4399

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Toll-free: 0800 171715  
Telephone +55 11 4166 8122  
Fax +55 11 4166 8720

---

**Asia Pacific**

DuPont China Holding Co, Ltd.  
15th Floor, Shui on Plaza  
333 Huai Hai Road (Central)  
Shanghai 200021, China  
Telephone +86 21 6386 6366  
Fax +86-21-6386-6333

DuPont K.K./DuPont Asia Pacific  
Sanno Park Tower  
11-1, Nagatacho 2-chome  
Chiyoda-ku, Tokyo, 100-611, Japan  
Telephone +81-3-5521-2771  
Fax +81-3-5521-2775

---

**Europe / Middle East Africa**

DuPont de Nemours Int'l.  
S.A. 2,  
Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone +41 22 717 51 11  
Fax +41 22 717 55 00

<http://www.dupont.com>

email: [pip@dupont.com](mailto:pip@dupont.com)

*Copyright © 2007 DuPont. All rights reserved. The technical data herein are guides to the use of DuPont resins. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary from lot to lot and with processing conditions. It is given and accepted at user's risk and confirmation of its validity and suitability in particular cases*

*This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see DuPont Medical Caution Statement, H-50102.*

*The DuPont Oval, DuPont™, The miracles of science™, and Surlyn®*

should be obtained independently. The DuPont Company makes no guarantees of results and assumes no obligations or liability in connection with its advice. are trademarks or registered trademarks of DuPont or its affiliates.

Copyright© 1995-2007. E.I. duPont de Nemours and Company. All Rights Reserved.

This data sheet is effective as of 08/09/2007 12:03:09 PM and supersedes all previous versions.

