

DuPont™ Surlyn® 1702-1

Surlyn® resins Product Data Sheet

Description

Product Description

Surlyn® 1702-1 is available for use in conventional blown, cast film, sheet extrusion and coextrusion equipment. It is also used in extrusion coating and coextrusion coating equipment designed to process polyethylene and ethylene copolymer type resins.

Restrictions

Material Status

- Commercial: Active

Typical Characteristics

Features

Zinc Ionomer

Typical Properties

Physical	Nominal Values	Test Method(s)	
Density ()	0.95 g/cm ³	ASTM D792	ISO 1183
Melt Flow Rate (190°C/2.16kg)	14.0 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
Melting Point (DSC)	94°C (201°F)	ASTM D3417	ISO 3146
Freezing Point (DSC)	67°C (153°F)	ASTM D3417	
Vicat Softening Point ()	65°C (149°F)	ASTM D1525	ISO 306

Processing Information

General

Maximum Processing Temperature 260°C (500°F)

General Processing Information

Surlyn® 1702-1 is normally processed at melt temperatures ranging from 160°-235°C (320°-455°F) in blown, cast and extrusion coating equipment. Typical extruder profiles are below. Actual processing temperatures will usually be determined by either the specific equipment or substrate or one of the other polymers in a coextrusion.

Materials of construction used in the processing of this resin should be corrosion resistant. Stainless steels of the types 316, 15-5PH, and 17-4PH are excellent, as is quality chrome or nickel plating, and in particular duplex chrome plating. Type 410 stainless steel is satisfactory, but needs to be tempered at a minimum temperature of 600°C (1112°F) to avoid hydrogen-assisted stress corrosion cracking. Alloy steels such as 4140 are borderline in performance. Carbon steels are not satisfactory. While stainless steels can provide adequate corrosion protection, in some cases severe purging difficulties have been encountered. Nickel plating has been satisfactory, but experiments have shown that chrome surfaces have the least adhesion to acid based polymers. In recent years, the quality of

chrome plating has been deteriorating due to environmental pressures, and the corrosion protection has not always been adequate. Chrome over top of stainless steel seems to provide the best combination for corrosion protection and ease of purging.

If surface properties of the extruded resin require modification (such as, lower C.o.F. for packaging machine processing), refer to the Conpol™ Processing Additive Resins product information guide.

After processing Surlyn®, purge the material out using a polyethylene resin, preferably with a lower melt flow rate than the Surlyn® resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your DuPont Sales Representative.

Never shut down the extrusion system with Surlyn® in the extruder and die. Properly purge out the Surlyn® with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

Blown Film Processing	Nominal Values
Blown Film Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	110°C (230°F)
Second Zone	135°C (275°F)
Third Zone	160°C (320°F)
Fourth Zone	160°C (320°F)
Fifth Zone	160°C (320°F)
Adapter Zone	160°C (320°F)
Die Zone	160°C (320°F)
Cast Film / Sheet Processing	Nominal Values
Cast Film Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	135°C (275°F)
Second Zone	185°C (365°F)
Third Zone	210°C (410°F)
Fourth Zone	210°C (410°F)
Fifth Zone	210°C (410°F)
Adapter Zone	210°C (410°F)
Die Zone	210°C (410°F)
Extrusion Coating/Lamination Processing	Nominal Values
Extrusion Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	160°C (320°F)
Second Zone	210°C (410°F)
Third Zone	235°C (455°F)
Fourth Zone	235°C (455°F)
Fifth Zone	235°C (455°F)
Adapter Zone	235°C (455°F)
Die Zone	235°C (455°F)

FDA Status Information

Surlyn® 1702-1 conforms to the United States Code of Federal Regulations, Title 21, Paragraph 177.1330 covering its use as a food contact surface subject to the extractives limitations on the finished food contact article as described in the regulation.

Regulatory Information

For information on regulatory compliance outside of the U.S., consult your local DuPont representative.

Safety & Handling

Surlyn® 1702-1 as supplied by DuPont are not considered hazardous materials. As with any hot material, care should be taken to protect the hands and other exposed parts of the body when handling molten polymer. At recommended processing temperatures, small amounts of fumes may evolve from the resins. When resins are overheated, more extensive decomposition may occur. Adequate ventilation should be provided to remove fumes from the work area. Disposal of scrap presents no special problems and can be by landfill or incineration in a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls. For more detailed information on the safe handling and disposal of DuPont resins, a Material Safety Data Sheet can be obtained from the DuPont Packaging and Industrial Polymers website or by contacting your sales representative.

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

DuPont Offices Worldwide

Americas

DuPont Company
Barley Mill Plaza 26-2363
Lancaster Pike & Route 141
Wilmington, DE 19880-0026 U.S.A.
Telephone +1 302-774-1161
Toll-free (USA) 800-628-6208 prompt "6"
Fax +1 302-999-4399

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Toll-free: 0800 171715
Telephone +55 11 4166 8122
Fax +55 11 4166 8720

Asia Pacific

DuPont China Holding Co, Ltd.
15th Floor, Shui on Plaza
333 Huai Hai Road (Central)
Shanghai 200021, China
Telephone +86 21 6386 6366
Fax +86-21-6386-6333

DuPont K.K./DuPont Asia Pacific
Sanno Park Tower
11-1, Nagatacho 2-chome
Chiyoda-ku, Tokyo, 100-611, Japan
Telephone +81-3-5521-2771
Fax +81-3-5521-2775

Europe / Middle East Africa

DuPont de Nemours Int'l.
S.A. 2,
Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

<http://www.dupont.com>

email: pip@dupont.com

Copyright © 2007 DuPont. All rights reserved. The technical data herein are guides to the use of DuPont resins. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary from lot to lot and with processing conditions. It is given and accepted at user's risk and confirmation of its validity and suitability in particular cases

This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see DuPont Medical Caution Statement, H-50102.

The DuPont Oval, DuPont™, The miracles of science™, and Surlyn®

should be obtained independently. The DuPont Company makes no guarantees of results and assumes no obligations or liability in connection with its advice. are trademarks or registered trademarks of DuPont or its affiliates.

Copyright© 1995-2007. E.I. duPont de Nemours and Company. All Rights Reserved.

This data sheet is effective as of 08/09/2007 12:04:06 PM and supersedes all previous versions.

