



# Surlyn®

thermoplastic resins

## Basic Description

DuPont *Surlyn*® brand resins are unique ionomer-class molding and extrusion materials created from DuPont proprietary acid copolymers. Starting with selected molecular weight grades of copolymers such as ethylene/methacrylic acid, DuPont adds zinc, sodium, lithium or other metal salts. Acid neutralization results in the formation of ion clusters (hence the general term, "ionomer") within the resulting polymer matrix.

*Surlyn*® resins are designed and manufactured by DuPont to deliver premium end-use performance or processing characteristics in a variety of specialized industrial applications.

## Performance Features

*Surlyn*® resins incorporate many of the performance features of the original ethylene-based copolymers, such as chemical resistance, melting range, density, and basic processing characteristics. However, *Surlyn*® resin performance is significantly enhanced in such areas as:

- low temperature impact toughness;
- abrasion/scuff resistant

- chemical resistance;
- transparency/clarity
- melt strength;
- direct adhesion of epoxy and polyurethane finishes; and
- direct adhesion to metal, glass, and natural fibers by heat lamination.

## Product Range

DuPont offers a wide selection of *Surlyn*® resins, starting with base resins of varying molecular weight. Proprietary manufacturing technologies allow precise control of acid levels and the degree of acid neutralization occurring with each metal ion type in each resin grade. This precision control enables DuPont to manufacture each grade of its *Surlyn*® product line with high lot-to-lot consistency and end-use reliability.

More than 30 grades of *Surlyn*® currently are available commercially for molding and industrial applications. The range of properties for these resins are shown in Table 1.

Table 1. Selected Properties of *Surlyn*®

Property	Value Range	Test Method
Specific Gravity	0.94 - 0.97	ASTM D 792
Hardness (Shore D)	36 - 68	ASTM D 2240
Flex Modulus (room temp, kpsi)	4.3 - 75	ASTM D790 Procedure B
Tensile Strength (kpsi)	2.3 - 5.4	ASTM D 638
Elongation at Break (%)	285 - 770	ASTM D 638
Melt Flow Index (g/10 min.)	0.7 - 20.0	ASTM D 1238
Vicat Softening Point (°C)	47 - 74	ASTM D 1525-70
Melting Point (°C)	70 - 100	DSC*
Freeze Point (°C)	38 - 75	DSC*
Optical Haze (0.25 in.(6.4 mm))	1.3 - 27	ASTM D1003A

\*As determined by differential scanning calorimetry

## For More Information

Complete properties for individual grades of *Surlyn*<sup>®</sup> thermoplastic resins for molding and industrial extrusion can be found on DuPont's web site.

DuPont technical staff are also available via e-mail and by mail, fax or telephone.

---

### DuPont Worldwide

Toll-free (U.S.A.) **800 438-7225**

---

#### United States

DuPont Packaging and Industrial Polymers  
Barley Mill Plaza 26-2122  
Lancaster Pike & Route 141  
P.O. Box 80026  
Wilmington, DE 19880-0026  
Telephone (302) 992-5225  
Fax (302) 992-3495

#### Canada

DuPont Canada Inc.  
P.O. Box 2200, Streetsville  
7070 Mississauga, Road  
Mississauga, ONT L5M 2H3  
Telephone (Canada Only):  
(800) 268 3943/(905) 821 5953  
Fax (905) 821 5230

#### Brazil/South America

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Telephone 55 (11) 7266 8542  
Fax 55 (11) 7266 8720

#### Mexico/Central America

DuPont, S.A. de C.V.  
Homero 206 Anexo Planta Alta  
Col. Chapultepec Morales  
11570, D.F. Mexico  
Telephone (525) 722 1000  
Fax (525) 722 1308

---

#### Europe

DuPont de Nemours Int'l. S.A.  
2, Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone (022) 717 51 11  
Fax (022) 717 55 00

#### Asia Pacific

DuPont Singapore PTE Ltd.  
1 Maritime Square #07-01  
World Trade Centre  
Singapore 0409  
Telephone (65) 273 2244  
Fax (65) 272 7494

#### Japan

Mitsui-DuPont  
Polychemicals Co., Ltd.  
Kasumigaseki Bldg. 24F  
3-2-5 Kasumigaseki  
Chiyoda-ku, Tokyo 100, Japan  
Telephone (813) 3580 5531  
Fax (813) 3592 1540

#### Australia

DuPont (Australia) Ltd.  
254 Canterbury Road  
Bayswater, Victoria 3153  
Australia  
Telephone (3) 9721 5900  
Fax (3) 9721 5650

---

#### Internet/World Wide Web:

<http://www.dupont.com/industrial-polymers>

#### E-Mail:

[industrial.polymers@dupont.com](mailto:industrial.polymers@dupont.com)

---

The technical data contained herein are guides to the use of DuPont resins. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary with processing conditions. It is given and accepted at user's risk and confirmation of its validity and suitability in particular cases should be obtained independently. The DuPont Company makes no guarantees of results and assumes no obligations or liability in connection with its advice. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents.

**CAUTION:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see DuPont Medical Caution Statement, H-50102.



# Surlyn<sup>®</sup>

Only by DuPont