

DuPont™ Teflon® PTFE TE-3876

Aqueous Fluoropolymers
made with
Echelon™ Dispersion Technology

Product Information

Aqueous Dispersion

Brand

Teflon® is a registered trademark of DuPont for its brand of fluoropolymer resins, which can only be licensed by DuPont for use in approved applications. Customers who wish to use the Teflon® trademark in connection with DuPont products under license from DuPont should either contact (800) 262-2745 in the US or the regional sales office listed at the back of this brochure. Without a license, customers may not identify their product as containing Teflon®, but may refer to the resin as PTFE fluoropolymer dispersion TE-3876.

Description

DuPont™ Teflon® PTFE TE-3876 fluoropolymer resin is a negatively charged, hydrophobic colloid, containing approximately 60% (by total weight) of 0.05 to 0.5 µm polytetrafluoroethylene (PTFE) resin particles suspended in water. Seen as a milky white liquid, it also contains approximately 6% (by weight of PTFE) of a non-ionic wetting agent and stabilizer. Viscosity at room temperature is approximately 25 cP (mPa·s). Nominal pH is 10.5.

DuPont™ Teflon® PTFE TE-3876 is recommended for coating applications on a variety of substrates. Compared to other products for such applications, Teflon® PTFE TE-3876 ex-

hibits, even at high temperature usage, improved durability, abrasion resistance, flex-life, gloss and color. These characteristics make it specially suited for topcoats in for example metal and glasscloth coatings.

DuPont™ Teflon® PTFE TE-3876 is based on new and improved polymer and formulation technologies that ensure higher product quality and processing improvements in various coating applications. Teflon® PTFE TE-3876 dispersion has improved shear resistance, hence is less prone to coagulation, and is therefore well suited to processes where high shear is present such as roller and curtain coatings. Other product improvements include higher gloss, mechanical strength and durability, while the processor benefits from improved Critical Cracking Thickness and improved sinterability, which lead to improved productivity and yields.

When properly processed, the PTFE resin in Teflon® PTFE TE-3876 exhibits the superior properties typical of the fluoropolymer resins: retention of properties after service at 260°C (500°F), useful properties at -240°C (-400°F), chemical inertness to nearly all industrial chemicals and solvents, and low friction and antistick surfaces. Dielectric properties are outstanding and stable with frequency and temperature. Refer to **Table 1** for typical property data.



The miracles of science™

FDA Compliance

Properly processed products (sintered at high temperatures common to the industry) made from Teflon® PTFE TE-3876 resin can qualify for use in contact with food in compliance with FDA Regulation 21 CFR 177.1550 and the German BGA. Products made from unsintered dispersion do not comply.

Processing

Conventional melt or solvent processing methods cannot be used to process PTFE. Techniques to make coatings or films from PTFE dispersions have been developed. These involve the adequate application of the PTFE or mixtures thereof onto a substrate, followed by drying and sintering at temperatures above the melting point of PTFE.

Metal Substrates

Conventional coating of substrates such as metals can be done in general by spraying or roller coatings, and in some cases by curtain coating. These techniques require PTFE dispersions which are resistant to shear, in other words, the primary particles of PTFE should not deform or agglomerate during the application step. This is particularly true for roller and curtain coating. Teflon® PTFE TE-3876 has been proven to provide improved stability resistance to such high shear process operations. The film on the substrate should be fault or defect free, and exhibit a smooth finished surface. In these aspects Teflon® PTFE TE-3876 has also been proven to be an excellent product.

Typical processing temperatures are as follows: application at room temperature, drying at 110° to 120°C, surfactant removal at 250° to 270°C and sintering at 360° to 380°C. The exact settings will depend on the particular process conditions, such as speed and loadings, on the product architecture and the equipment used.

Fabric Substrates

Teflon® PTFE TE-3876 is also suitable for coating or impregnating of other materials, such as glasscloth. It is specifically designed for use as a topcoat for improved gloss and release properties. Conventional dip or flow techniques can be used for coating or impregnating other products with Teflon® PTFE TE-3876. The resin particles can be consolidated by heat into a coherent matrix or coating or left as particles to influence the properties of a finished product.

A continuous PTFE resin coating on woven fabrics can be made by dip coating. Successive passes must be used to build up thickness slowly and without cracks. Teflon® PTFE TE-3876 fluoropolymer provides good rewetting on each pass and void-free buildup suitable for more demanding electrical and chemical service applications. Each coating layer is usually dried to remove water (typically at 120°C), baked to remove the wetting agent (typically at 250–290°C),

and finally heated above the crystalline melting point of the resin particles (approximately 337°C). A calendering process may be used after the fabric has been baked in applications where multiple passes of PTFE need to be consolidated prior to sintering. Glass, PTFE, Nomex® aramid fiber, Kevlar® aramid fiber, or other high-temperature resistant fibers must be used.

The excellent shear stability of Teflon® PTFE TE-3876 may also provide increases in productivity, yield, and quality.

Other solid or liquid ingredients can be added to Teflon® PTFE TE-3876 to provide specific processing or finished product behavior.

Safety Precautions

WARNING!

VAPORS CAN BE LIBERATED THAT MAY BE HAZARDOUS IF INHALED.

Before using Teflon® PTFE TE-3876, read the Material Safety Data Sheet and the detailed information in the "Guide to the Safe Handling of Fluoropolymer Resins," latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry or the "Safe handling of Fluoropolymer dispersions" published by the APME. These documents are available from DuPont.

Open and use containers only in well-ventilated areas using local exhaust ventilation (LEV). Vapors and fumes liberated during hot processing, or from smoking tobacco or cigarettes contaminated with Teflon® PTFE TE-3876 fluoropolymer resin, may cause flu-like symptoms (chills, fever, sore throat) that may not occur until several hours after exposure and pass within about 24 hours. Vapors and fumes liberated during hot processing should be exhausted completely from the work area; contamination of tobacco with polymers should be avoided.

Mixtures with some finely divided metals, such as magnesium or aluminum, can be flammable or explosive under some conditions.

Teflon® PTFE TE-3876 contains additives in the aqueous phase that are irritants. In case of skin contact, flush with water immediately. In case of eye contact, flush with water immediately and get medical help.

Storage and Handling

The dispersion particles in Teflon® PTFE TE-3876 will settle on prolonged standing or on heating above 66°C (150°F). They usually can be redispersed by mild agitation. Drums may be rolled or the product stirred gently just prior to use. The dispersion must be protected from freezing, which will cause irreversible settling.

Ammonium hydroxide is used by DuPont to set pH to 10 at the time of shipment. High ambient temperatures can deplete the ammonia level and reduce the pH. Declining pH eventually favors bacterial growth, which causes odor and scum. The pH should be measured and maintained between 9.5 and 10.5.

Both very high and very low temperatures may be detrimental. Dispersions must not be allowed to freeze. The optimum storage temperature range is 7–24°C (45–77°F), with temperatures low in the range preferred. Storage at 7–32°C (45–90°F) is acceptable within nominal shelf life for standard dispersions. If dispersions are to be stored for extended periods beyond their nominal shelf life, low-temperature storage is especially desirable because the particles are harder at lower temperatures and, therefore, are less likely to stick together as they settle.

High-speed stirring, pumping, or any other violent agitation must be avoided to minimize sheared particles or coagulation and to minimize foaming. Ideally, the dispersion should be conveyed by gravity from storage to processing stations.

Storage and handling areas should be clean. Keep dispersion drums closed and clean to avoid both contamination and coagulation by drying at the liquid surface. High processing temperatures will cause even very small foreign particles to become visible or to make defects in finished products. Good housekeeping and careful handling are essential.

Packaging

In the United States, Teflon® PTFE TE-3876 is packaged in 19- and 114-L (5- and 30-gal) non-returnable drums and 1037-L (275-gal) recyclable containers. In Europe, Teflon® PTFE TE-3876 is packaged in 30-L (8-gal) nonreturnable drums and 1000-L (263 gal) recyclable containers. Contact the local DuPont sales office for package sizes available in your specific geographic area.

Freight Classification

Teflon® PTFE TE-3876, when shipped by rail or express, is classified “Plastics, Synthetic, Liquid, NOIBN.” Resin shipped by truck is classified “Plastics, Materials, Liquid, NOI.”

Table 1
Typical Property Data for DuPont™ Teflon® PTFE Fluoropolymer Resin Dispersion Grade TE-3876

Typical Property Data for Teflon® TE-3876

Property	Test Method ⁽¹⁾		Unit	Typical Value
General				
Solids Content (% PTFE by weight)	ISO 12086	D 4441	%	60
Density of Dispersion (at 60% solids)	ISO 8962	D 4441	g/cm ³	1.50
Resin Dry Weight (at 60% solids)		DuPont	g/l (lbs/gal)	900 (7.5)
Color				White
Dispersion Particle Size, average diameter	ISO 13321	DuPont	µm	0.270
pH of Dispersion	ISO 976	E 70		10.5
Brookfield Viscosity (at 25°C)	ISO 2555	D 2196	mPa·s (cP)	25 (25)
Standard Specific Gravity of Sintered Resin	ISO 12086			2.220
Thermal ⁽²⁾				
Initial Melt, Peak Temperature		D4895	°C (°F)	344 (653)
Second Melt, Peak Temperature		D4895	°C (°F)	327 (621)
Brittleness Temperature		D 746	°C	< -75
Continuous Service Temperature (max)			°C	260
Other ⁽²⁾				
Weather and Chemical Resistance				Excellent

Note: Teflon® TE-3876 meets the requirements of ASTM D 4441-04, type II, grade 6, class B.

Typical properties are not suitable for specification purposes.

Decimals are indicated by a period (.)

⁽¹⁾ ASTM unless otherwise specified.

⁽²⁾ These results are based on tests made on thin cast films.

For more information call (302) 479-7731

www.teflon.com

**DuPont Fluoroproducts
P.O. Box 80713
Wilmington, DE 19880-0713**

Europe

DuPont de Nemours Int'l SA
DuPont Fluoroproducts
2, chemin du Pavillon
P.O. Box 50
CH-1218 Le Grand-Saconnex
Geneva, Switzerland

Japan

DuPont Mitsui Fluorochemicals
Co., Ltd.
Chiyoda Honsha Building
5-18, Sarugaku-cho 1-chome
Chiyoda-ku, Tokyo 101 Japan
81-3-5281-5872

Asia Pacific

DuPont China, Limited
26/F., Tower 6, The Gateway
9 Canton Road, Tsimshatsui
Kowloon, Hong Kong
(852) 27341948
Tim-S.T.Leung@hkg.dupont.com

Canada

DuPont Canada, Inc.
DuPont Fluoroproducts
P.O. Box 2200, Streetsville
7070 Mississauga Road
Mississauga, Ontario, Canada
L5M 2H3
(800) 207-0756

South America

DuPont do Brasil S/A
Fluoropolymers
Alameda Itapecuru, 506
06454-080 - Alphaville
P.O. Box 263
Barueri, Sao Paulo, Brazil
0800-171715
Produtos.Brazil@bra.dupont.com

Copyright © 2006 DuPont or its affiliates. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™, Nomex®, Kevlar®, and Teflon®, are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body or contact with internal body fluids or tissues. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

