













0799-CPD



# Typar SF27

DuPont de Nemours (Luxembourg) S.à.r.l.  
 Typar® Geosynthetics  
 L-2984 Luxembourg  
 09

0799-CPD-12

Applications				
				
Road construction and other trafficked areas EN 13249 : 2000	Railways EN 13250 : 2000	Earthworks, foundations and retaining structures EN 13251 : 2000	Drainage systems EN 13252 : 2000	Erosion control EN 13253 : 2000

				
Reservoirs and dams EN 13254 : 2000	Canals EN 13255 : 2000	Tunnels and underground structures EN 13256 : 2000	Solid waste disposals EN 13257 : 2000	Liquid waste disposals EN 13265 : 2000

Intended uses	Filtration	Filtration + Separation
		

Properties	Test Method	Unit	Mean Value	Tolerances
Tensile Strength	EN ISO 10319	kN/m	MD 4.7	- 0.61
			CMD 5.3	- 0.69
Dynamic Perforation Resistance (Cone Drop)	EN ISO 13433	mm	45	+ 5
Resistance to Static Puncture	EN ISO 12236	kN	0.750	- 0.075
Opening Size	EN ISO 12956	µm	175	± 52.5
Water Permeability	EN ISO 11058	m/s	100 • 10 <sup>-3</sup>	- 30 • 10 <sup>-3</sup>
Durability	To be covered within 2 weeks after installation Predicted to be durable for a minimum of 100 years in all natural soils.			
Oxydation Resistance	prEN ISO 13438	Retained strength	MD 100 % CMD 100 %	
Chemical Resistance	EN 14030	Retained strength	MD 100 % CMD 100 %	
Microbiological Resistance	EN 12225	Retained strength	MD 100 % CMD 100 %	