













0799-CPD



Typar SF56

DuPont de Nemours (Luxembourg) S.à.r.l.
 Typar® Geosynthetics
 L-2984 Luxembourg
 09

0799-CPD-12

Applications				
				
Road construction and other trafficked areas EN 13249 : 2000	Railways EN 13250 : 2000	Earthworks, foundations and retaining structures EN 13251 : 2000	Drainage systems EN 13252 : 2000	Erosion control EN 13253 : 2000

				
Reservoirs and dams EN 13254 : 2000	Canals EN 13255 : 2000	Tunnels and underground structures EN 13256 : 2000	Solid waste disposals EN 13257 : 2000	Liquid waste disposals EN 13265 : 2000

Intended uses	Filtration	Filtration + Separation
		

Properties	Test Method	Unit	Mean Value	Tolerances
Tensile Strength	EN ISO 10319	kN/m	MD 13.1	- 1.7
			CMD 13.1	- 1.7
Dynamic Perforation Resistance (Cone Drop)	EN ISO 13433	mm	22	+ 4.4
Resistance to Static Puncture	EN ISO 12236	kN	1.850	- 0.185
Opening Size	EN ISO 12956	µm	80	± 24
Water Permeability	EN ISO 11058	m/s	$35 \cdot 10^{-3}$	$- 10 \cdot 10^{-3}$
Durability	To be covered within 2 weeks after installation Predicted to be durable for a minimum of 100 years in all natural soils.			
Oxydation Resistance	prEN ISO 13438	Retained strength	MD 100 %	
			CMD 100 %	
Chemical Resistance	EN 14030	Retained strength	MD 100 %	
			CMD 100 %	
Microbiological Resistance	EN 12225	Retained strength	MD 100 %	
			CMD 100 %	