



The miracles of science™



CPD 89/106




## Style 8327AD

Type of carrier: Polypropylene & Ethylen-Butylacrylate Copolymer

DuPont de Nemours (Luxembourg) s.à r.l.  
L-2984 Luxembourg

# Technical Data Sheet

Language: English  
Applicable for: all over Europe  
Effective Date: 24.01.2007

		<u>Application:</u> Plastic and rubber vapour control layers  <b>EN 13984</b> (Dec. 2004)
	<u>Product designation:</u>  <b>Type B</b>	

PROPERTY	METHOD	UNITS	NOMINAL (Mean value)	TOLERANCE	
				Minimum	Maximum
Length (expressed in m)	EN 1848-2	%	Customer related	0	-
Width (expressed in mm)	EN 1848-2	%	Customer related	0,5	1,5
Straightness	EN 1848-2	mm	-	-	75
Mass per unit area	EN 1849-2	gr/m <sup>2</sup>	108	100	116
Thickness	EN1849-2	mm	0,3	0,23	0,37
Water tightness	EN 1928 (method A)	pass / no pass	NPD	-	-
Water vapour resistance	EN 1931	m	5	2	10
Maximum tensile force (MD)	EN 12311-2	N/50mm	200	160	-
Elongation at max. tensile force (MD)	EN 12311-2	%	38	25	-
Maximum tensile force (XD)	EN 12311-2	N/50mm	170	110	-
Elongation at max. tensile force (XD)	EN 12311-2	%	38	23	-
Resistance to tearing MD (nail shank)	EN 12310-1	N	240	180	-
Resistance to tearing XD (nail shank)	EN 12310-1	N	240	180	-
Resistance to impact	EN 12691	mm	NPD	-	-
Reaction to fire	EN 11925-2	class	E	-	-
Joint strength	EN 12317-2	N/5cm	NPD	-	-
Durability (exposure to artificial ageing)		Residual value	Aged/new material		
Water vapour resistance	EN 1931	%	70	-	-
Durability (against alkali)		Residual value	Aged/new material		
Elongation at max. tensile force (MD)	EN 12311-2	%	NPD	-	-
Elongation at max. tensile force (XD)	EN 12311-2	%	NPD	-	-
<b>ADDITIONAL PROPERTIES</b>					
Bendtsen airpermeability	ISO 5636/6	ml/min	0	-	-
Gurley airpermeability	ISO 5636/5	s	-	> 2000	∞

Some test methods are modified according to the EN 13984 and/or according to the DuPont DIN EN ISO 9001 (2000) certified quality system (for details please contact your regional DuPont representative). This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentation. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature

The DuPont Oval, DuPont™, The miracles of sciences & Tyvek are registered trademarks or trademarks of DuPont or its affiliates

Address:  
Rue Général Patton, Contern  
L-2984 Luxembourg

Tyvek® Marketing  
Tyvek® Customer Service  
Tyvek® Manufacturing

Fax (00352) 3666 5021  
Fax (00352) 3666 5018  
Fax (00352) 3666 5020