

PROPERTIES	METHOD	DUPONT™ TYVEK® DRAINWRAP™ weather-resistive barrier
Air Penetration	Air-Ins (cfm/ft²@75 Pa)	.004
	Gurley Hill (TAPPI T-460) (sec/100cc)	300
	ASTM E-1677	Type 1
Water Vapor Transmission	ASTM E-96 Method B (g/m²·24 hrs) (perms)	350 50
	Water Penetration Resistance	AATCC-127 (cm)
Basis Weight	TAPPI T-41D (oz/yd²)	2.1
Breaking Strength	ASTM D-882 Method A (lbs/in)	30/30
Tear Resistance (trapezoid)	ASTM D-1117 (lbs)	7/9
Surface Burning Characteristics	ASTM E-84-97a Flame Spread	5 Class A
	Indexed Smoke Developed Value	25 Class A
Ultra Violet Light Exposure (UV)		120 days (4 months)

WARNING: Tyvek® is combustible and should be protected from a flame and other high heat sources. If the temperature of Tyvek® reaches 750 F (400 C), it will burn and the fire may spread and fall away from the point of ignition.

For more information:

1-800-44-TYVEK®
www.tyvek.com

DuPont™
Tyvek®
DrainWrap™



The miracles of science™