

Property		English Units	SI Units
Spec Grav		1.44	1.44
Tensile Strength	Kpsi (Mpa)	8.9	62
Elongation	%	4.7	4.7
CTE	uin/in/F (ppm/C)	41	23.5
COF - 25,000	PV	0.18	0.18
COF - 100,000	PV	0.09	0.09
Typical PV Limit	psi-fpm (Mpa M/S)	>600,000	>21,000